

Cretex[®] CR

**Resilient chemical resistant
concrete repair compound**



“maintenance made easy”



PRODUCT DESCRIPTION

Cretex CR is a three part polyurethane-based floor repair compound. This versatile product may be mixed to either a trowellable or pourable consistency and is easier to apply than epoxy equivalents, has low odour and cures rapidly for early return to serviceability. It offers excellent resistance to abrasion, impact and vibration, combining slight flexibility with exceptional toughness. Cretex CR is also highly resistant to a wide range of chemicals.

TYPICAL USES

Cretex CR is ideal for heavy duty concrete floor repairs that require impact or chemical resistance and is very suitable for use in engineering, chemical plants, food factories, breweries and areas of heavy plant traffic. Other uses include levelling, bonding paving and edging, grouting and bedding ceramic tiles, bolt grouting and as a waterproof mortar.

SUITABLE SUBSTRATES

Cretex CR is primarily designed for application to sound, dry concrete. For any other substrates please contact Polycote Technical Helpline.

COLOUR

Cretex CR is grey in colour.

PACKAGING

Cretex CR is supplied in pre-measured quantities as a three part 10.0kg unit comprising resin *Part 'A'*, hardener *Part 'B'* and fillers *Part 'C'*.

DIRECTIONS FOR USE

SURFACE PREPARATION

THOROUGH SUBSTRATE PREPARATION IS ESSENTIAL.

Remove all loose material – wire brushing is advisable. Sweep clean or vacuum. The surface must be free from grease, oil or other contamination. A gas torch will help to remove oil from the surface.

PRIMING

Cretex CR will bond to most concrete surfaces (including slightly damp, but not wet), without the need for priming. However, very dry, porous surfaces will need priming with *Cretex CR Primer*.

DIRECTIONS FOR USE

MIXING

Having prepared the substrate, add hardener **Part 'B'** to resin **Part 'A'** and mix thoroughly for at least one minute. For best results use a heavy duty slow speed drill with a mixing paddle.

ENSURE THOROUGH MIXING AS AN UNMIXED PRODUCT WILL RESULT IN A POOR OR NON-CURE SITUATION.

Pour the mixed liquid into a large plastic bucket and gradually add the filler **Part 'C'**, continuing to mix until an even consistency is achieved at the desired thickness:

For a trowellable mix – add the entire quantity of filler Part 'C'.

For a pourable mix – add HALF the quantity of filler Part 'C'. This will produce a grout-like consistency ideal for pouring into smaller repairs.

APPLICATION

Apply the material immediately after mixing, using a trowel or float. *Cretext CR* may be applied at 2mm minimum.

For supporting vertical repairs – where step nosings or expansion joint edges have broken away, the vertical face of the repair material should be supported to prevent slumping.

Suitable sized wooden shuttering should be covered with polythene to reduce adhesion, and should be removed as soon as the material is firm.

POT LIFE & CURING TIMES

The pot life is 10-15 minutes depending on temperature.

At 10mm thickness and at 20°C *Cretext CR* can take light foot traffic after 4 to 5 hours and light forklift

traffic after 6 hours. *Cretext CR* will cure at temperatures down to 5°C but times will be greatly extended.

TEMPERATURE

Ideal application temperature range is between 15°C and 25°C. The substrate and uncured floor must be kept at least 3°C above the dew point to reduce the risk of condensation or blooming on the surface for at least 48 hours after application.

APPLICATION THICKNESS

The recommended range of application thickness is from 5mm to 10mm.

COVERAGE

The coverage rate per 10kg unit of *Cretext CR* is approximately 1m² at 5mm nominal thickness.

CLEANING

Tools and equipment should be cleaned whilst resin is still wet with warm soapy water.

Hands and skin should be cleaned immediately with Organic Hand Cleaner.

SHELF LIFE & STORAGE

Shelf life is 6 months subject to storage conditions being above +10°C and continuously dry. Protect from frost.



Polycote UK, Centre Point, Wolseley Road,
Woburn Road Industrial Estate, Kempston,
Beds MK42 7EF

13

EN 13813 SR-B1,5-AR0,5-IR20

Synthetic resin screed material for use internally in buildings not subject to reaction to fire regulations

Reaction to fire:	NPD
Release of corrosive substances:	SR
Water permeability:	NPD
Wear resistance:	AR0,5
Bond strength:	B1,5
Impact resistance:	IR20
Sound insulation	NPD
Sound absorption	NPD
Thermal resistance	NPD
Chemical resistance	NPD

HEALTH & SAFETY

Before using this product, please ensure you have received and read carefully both the Hazard Label applied to the container and the relevant Material Safety Data Sheets.

ANY QUESTIONS?

Please do not hesitate to contact us for advice regarding the use of this product or its suitability for your particular application. Our aim is to provide all the technical help you need to make an informed choice and achieve total success.

Polycote Technical Helpline
01234 846400

All reasonable care has been taken in supplying the above information. However, any figures quoted do not constitute a specification but represent typical values obtained. It is the customer's responsibility to ensure for himself that the product is fit for the intended purpose and that conditions are suitable. Any technical advice is offered in good faith, but without warranty. This is also applicable when proprietary rights and third parties are involved. In the light of the Company's policy of continual research and development, it is the customer's responsibility to ensure that the information contained herein has not been superseded.

REV: 06/17