

# WD Primer

**High adhesion water-dispersed epoxy primer**



**“maintenance made easy”**



## PRODUCT DESCRIPTION

**WD Primer is a two part water dispersed 50% solids specialist epoxy floor primer providing a dustproof coating resistant to oils and chemicals. It will provide a tough, hard-wearing protective floor finish with a semi-gloss/silk finish that is economical and easy to apply.**

### TYPICAL USES

WD Primer has been specially formulated to adhere to impervious surfaces, providing a primer coat for a wide range of Polycote epoxy top coats. Being solvent-free, taint-free, odourless and non-toxic, WD Primer is ideal for use in medical, animal, food-processing and working environments. Typical applications include warehouses, factories, workshops, commercial kitchens, laboratories and chemical bunds.

### SUITABLE SUBSTRATES

WD Primer may be applied to old and new concrete and polymer modified cementitious screeds.

### COLOUR

WD Primer is white when applied, but dries to a clear finish.

### PACKAGING

WD Primer is supplied in pre-measured quantities as a two part 5.0kg unit, comprising an epoxy resin blend Part 'A' and hardener Part 'B'.

## DIRECTIONS FOR USE

### SURFACE PREPARATION

**THOROUGH SUBSTRATE PREPARATION IS ESSENTIAL.**

Recommended methods are:

**Powerfloated concrete** – use a Vacuum Assisted Shotblaster to remove weak laitence and provide a surface key for the coating. If this is not possible, chemically etch with *Polycote Etch IT* then rinse thoroughly and allow to dry.

**Loose paint or rust** – remove, using a Vacuum Assisted Shotblaster, Floor Grinder or equivalent method.

**Loose or friable concrete** – use a Vacuum Assisted Shotblaster. If this is not possible, chemically clean with *Polycote Etch IT* then rinse thoroughly and allow to dry.

**Oil or grease** – use Hot Compressed Air for large areas of contamination. Smaller, isolated deposits may be chemically cleaned with *Polycote Degrease IT*, then rinsed thoroughly and allowed to dry.

**DIRECTIONS FOR USE Cont.**

See relevant Data Sheet prior to application.

**ONCE PREPARED, THE AREA MUST BE KEPT CLEAN AND FREE OF TRAFFIC.**

**MIXING**

Having fully prepared the substrate, stir the individual components before mixing together. Add Part 'B' to Part 'A' and thoroughly mix for at least 3 minutes. For best results use a heavy duty slow speed drill with a mixing paddle.

**ENSURE THOROUGH MIXING AS AN UNMIXED PRODUCT WILL RESULT IN A POOR OR NON-CURE SITUATION.**

**APPLICATION**

Prior to application of epoxy coatings – apply *WD Primer* by brush, roller or squeegee, making sure that the surface is completely covered. Particular attention should be given to doorways and other areas of high traffic. When finished, **DO NOT** scrape the remaining contents from the container as this will invariably include unmixed raw resin.

**IMPORTANT** – Ensure thorough coverage of porous surfaces, working the primer well into the surface. Failure to do this may allow the floor to 'breathe' and result in pinholing or bubbles in the epoxy top coat.

Prior to application of cementitious screeds – apply as above, then sprinkle kiln-dried quartz (ideally 0.3-0.6mm) onto the **WET** primer to provide a mechanical key and allow to cure. Any loose quartz should then be brushed off before laying the screed.

**POT LIFE AND CURING TIME**

The pot life is approximately 60 minutes at 20°C. Overcoating period is 8-24 hours. Light pedestrian traffic 24 hours and medium traffic is 48-72 hours. Full strength is reached after 7 days. The material should be protected from contact with water for 7 days.

**APPLICATION TEMPERATURE**

Normal application temperature range is between +10°C and +25°C.

To reduce the risk of 'blooming' caused by condensation, the climate above the uncured floor should be maintained at least 3°C above the dew point for at least 48 hours after application.

The substrate should be surface dry with a maximum relative humidity of 80%.

**COVERAGE**

The coverage of *WD Primer* is approximately 25-30m<sup>2</sup> per 5.0kg unit, depending on the texture and porosity of the surface.

**CLEANING**

Tools and equipment should be cleaned whilst resin is still wet using cold water.

Hands and skin should be cleaned immediately with Organic Hand Cleaner.

**SHELF LIFE & STORAGE**

Shelf life in unopened containers is approximately 12 months subject to conditions of storage.

Store in a cool, dry, frost-free environment between 15°C and 20°C and out of direct sunlight.

**CE**

Polycote UK, Centre Point, Wolseley Road,  
Woburn Road Industrial Estate, Kempston,  
Beds MK42 7EF

13

**EN 13813 SR-B2, 0-AR0, 5-IR5**

Synthetic resin screed material for use internally in buildings not subject to reaction to fire regulations

Wear resistance:	AR 0.5
Bond strength:	B 2.0
Impact resistance:	IR 5

**HEALTH & SAFETY**

**Before using this product, please ensure you have received and read carefully both the Hazard Label applied to the container and the relevant Material Safety Data Sheets.**

**ANY QUESTIONS?**

Polycote Technical Helpline  
**01234 846400**

All reasonable care has been taken in supplying the above information. However, any figures quoted do not constitute a specification but represent typical values obtained. It is the customer's responsibility to ensure for himself that the product is fit for the intended purpose and that conditions are suitable. Any technical advice is offered in good faith, but without warranty. This is also applicable when proprietary rights and third parties are involved. In the light of the Company's policy of continual research and development, it is the customer's responsibility to ensure that the information contained herein has not been superseded.

**REV: 11/17**

**Polycote UK**  
**Centre Point • Wolseley Road**  
**Woburn Road Industrial Estate**  
**Kempston • Beds • MK42 7EF**  
**Technical Helpline: 01234 846400**

**CE**

**POLYCOTE®**  
Est. 1991

**"maintenance made easy"**