

Flortex[®] MC Standard



Very fast curing low temperature floor coating

“maintenance made easy”



PRODUCT DESCRIPTION

Flortex[®] MC is an extremely hard-wearing methacrylate based high build resin floor coating. It can be applied at very low temperatures and cures with outstanding rapidity, enabling application with minimal downtime. Two grades are available: Flortex[®] MC Standard for fast curing at normal temperatures; and Flortex[®] MC CSG for temperatures down to -40°C. Please specify when ordering.

TYPICAL USES

Flortex[®] MC is suitable for almost any floor coating situation, particularly where rapid installation and long term durability are paramount. Flortex[®] MC CSG is primarily used in cold stores and industrial refrigerators and freezer floors.

SUITABLE SUBSTRATES

Flortex[®] MC is designed for application to concrete surfaces.

COLOUR

Flortex[®] MC is available in a range of 7 colours.

PACKAGING

Flortex[®] MC is supplied in pre-measured quantities as a three part system, comprising of a 5 litre unit of acrylic resin Part 'A', a powder hardener Part 'B', plus a separate pigment pack Part 'C'.

COLOUR GUIDE

7 Standard Colours available			
05	09	22	61
64	75	45	

Colours indicated are approximate and should not be taken as exact shade.

DIRECTIONS FOR USE

SURFACE PREPARATION

The substrate should be prepared and primed with Polycote *MC Primer*.

See relevant Data Sheet for full recommendations on preparation and priming.

MIXING

BEFORE MIXING THIS PRODUCT YOU MUST BE TOTALLY PREPARED for rapid uninterrupted application of the complete mixed quantity WITHIN 15 MINUTES.

Thoroughly shake the bottle of resin to ensure total dispersion of the contents, then pour into a clean, plastic bucket. Add the powder pigment and stir thoroughly using a heavy duty slow speed drill with mixing paddle. When the pigment is fully dispersed add the powdered Hardener and disperse.

ENSURE THOROUGH MIXING AS AN UNMIXED PRODUCT WILL RESULT IN A POOR OR NON-CURE SITUATION.

APPLICATION

Once the product is thoroughly mixed, APPLY IMMEDIATELY using a brush or roller, making sure the area is completely covered. Particular attention should be given to doorways and other areas of high traffic. When finished, **DO NOT** scrape the remaining contents from the container as this will invariably include unmixed raw resin.

NON-SLIP APPLICATIONS

For slip resistance, Calcined Bauxite aggregate may be sprinkled into the wet PRIMER. Please refer to MC Primer Data Sheet.

POT LIFE & CURING TIME

The pot life is **maximum** 15 minutes. Initial curing takes place within 1-1½ hours. Very low temperatures will extend the curing time.

APPLICATION TEMPERATURE

Flortex® MC is available in two temperature grades: *Standard Grade* for 0°C to +30°C application temperature, and *Cold Store Grade* for 0°C to -40°C.

COVERAGE

The coverage of *Flortex® MC* is between 15-20m² per 5 litre unit, depending on the texture and porosity of the substrate.

CLEANING

Tools and equipment should be cleaned whilst product is still wet using Polycote *Solvent Cleaner*. Hands and skin should be cleaned immediately with organic hand cleaner.

SHELF LIFE & STORAGE

Shelf life in unopened containers is approximately 12 months subject to conditions of storage.

Store in a cool, dry, frost-free environment away from sources of ignition.

HEALTH & SAFETY

Before using this product, please ensure you have received and read carefully both the Hazard Label applied to the container and the relevant Material Safety Data Sheets.

ANY QUESTIONS?

Please do not hesitate to contact us for advice regarding the use of this product or its suitability for your particular application. Our aim is to provide all the technical help you need to make an informed choice and achieve total success.

Polycote Technical Helpline
01234 846400

All reasonable care has been taken in supplying the above information. However, any figures quoted do not constitute a specification but represent typical values obtained. It is the customer's responsibility to ensure for himself that the product is fit for the intended purpose and that conditions are suitable. Any technical advice is offered in good faith, but without warranty. This is also applicable when proprietary rights and third parties are involved. In the light of the Company's policy of continual research and development, it is the customer's responsibility to ensure that the information contained herein has not been superseded.

REV: 03/18