

# Cretex<sup>®</sup> DPM Mortar

**Extremely tough, three-part epoxy mortar for damp surfaces**



**“maintenance made easy”**



## PRODUCT DESCRIPTION

***Cretex DPM Mortar is an extremely tough three-part epoxy mortar. It is ideal for patching and repairing large areas prior to overlaying with a floor coating. It is extremely easy to use and can be over-coated in only 3-4 hours. A primer is not generally required.***

***Cretex DPM Mortar is solvent free, non toxic and non taint and can therefore be used in food environments. It will also withstand very heavy traffic.***

### TYPICAL USES

*Cretex DPM Mortar is ideal for almost any floor repair and is particularly good for levelling large areas. It is ideal for use in factories, aircraft hangars, railway maintenance depots, food factories, car workshops, engineering plants, and many other areas.*

### SUITABLE SUBSTRATES

*Cretex DPM Mortar may be applied to most hard/porous building materials including concrete, breeze block, brick and stone.*

### PACKAGING

*Cretex DPM Mortar is supplied as a three part epoxy mortar in a 30kg unit.*

## DIRECTIONS FOR USE

### SURFACE PREPARATION

***THOROUGH SUBSTRATE PREPARATION IS ESSENTIAL.***

Remove all loose material. Wire brushing is advisable. Sweep clean or vacuum.

The surface must be free from grease, oil or contamination. Polycote *Degrease IT* may be used to clean the area but this must be thoroughly rinsed off and the substrate dried, before applying *Cretex DPM Mortar*.

**DIRECTIONS FOR USE Cont.****MIXING**

Having fully prepared the substrate, add the whole of Part B to the whole of Part A and mix thoroughly for at least 3 minutes. For best results use a slow speed drill with a mixing paddle. Finally, pour the liquid into the large bucket and add the aggregate to the desired consistency.

**ENSURE THOROUGH MIXING AS AN UNMIXED PRODUCT WILL RESULT IN A POOR OR NON-CURE SITUATION.**

**APPLICATION**

Apply by trowel, or by hand for small isolated areas, wearing suitable protective gloves.

Being resin-rich, *Cretex DPM Mortar* has a typically sticky consistency and smoothing may be assisted by wetting the trowel using Polycote Solvent Cleaner as a release agent.

If when trowelling the mortar the texture remains 'open' this can be easily 'closed' by slightly tamping the surface with the trowel. This can provide an extremely hard wearing and completely sealed surface.

**For vertical repairs** – where step nosings or expansion joint edges have broken away, the vertical face of the repair material should be supported to prevent slumping.

Suitable sized wooden shuttering should be covered with polythene to reduce adhesion, and should be removed as soon as the material is firm.

**POT LIFE & CURING TIMES**

The pot life of *Cretex DPM Mortar* once mixed is approx. 15 minutes.

**Important:** If the mix is not used within the pot life it will generate heat and may generate fumes through the reaction process.

Can be overcoated after 4 hours or once surface has lost tackiness.

Initial curing takes place within 6-8 hours depending on temperature.

Full strength is achieved after 7 days.

**APPLICATION TEMPERATURE**

Normal application temperature is between 10°C and 25°C.

**APPLICATION THICKNESS**

*Cretex DPM Mortar* can be laid to any thickness, however when feather-edging, add less aggregate to give a more resin rich formulation.

**COVERAGE**

The coverage rate per 30kg unit is 3m<sup>2</sup> at 5mm nominal thickness.

**CLEANING**

Tools and equipment should be cleaned whilst resin is still wet with Solvent Cleaner.

Hands and skin should be cleaned immediately with Organic Hand Cleaner.

**SHELF LIFE AND STORAGE**

Shelf life in unopened containers is approximately 12 months subject to conditions of storage.

Store in a cool, dry, frost-free environment away from sources of ignition, sealing the surface for protection against oil and other spillages.

**HEALTH & SAFETY**

**Before using this product, please ensure you have received and read carefully both the Hazard Label applied to the container and the relevant Material Safety Data Sheets.**

**ANY QUESTIONS?**

Polycote Technical Helpline  
**01234 846400**

All reasonable care has been taken in supplying the above information. However, any figures quoted do not constitute a specification but represent typical values obtained. It is the customer's responsibility to ensure for himself that the product is fit for the intended purpose and that conditions are suitable. Any technical advice is offered in good faith, but without warranty. This is also applicable when proprietary rights and third parties are involved. In the light of the Company's policy of continual research and development, it is the customer's responsibility to ensure that the information contained herein has not been superseded.

REV: 01/15

**Polycote UK**  
Centre Point • Wolseley Road  
Woburn Road Industrial Estate  
Kempston • Beds • MK42 7EF  
Technical Helpline: 01234 846400

CE

**POLYCOTE®**  
Est. 1991

**"maintenance made easy"**